



Deutsch: **Technisches Datenblatt** TPE 10° A

0601	TPE 10° A - super weich; Stärke: 2 - 8 mm	Stand: 07.12.2020
<b>Härte:</b>	10° ± 5° Shore A; 8° Shore A (ISO 868 (3 sec.))	
<b>Dichte (DIN EN ISO 1183-1A):</b>	0,99 g/ cm <sup>3</sup>	
<b>Farbe:</b>	Schwarz; Farbe möglich	
<b>Beständigkeiten:</b>	Ozon, Witterung, UV-Strahlung: gut <u>Öle und Fette:</u> ° pflanzliche: bedingt, ° tierische: bedingt – nein, ° mineralische: nein Säuren, Basen, Alkohol: gut – bedingt Kraftstoffe: nein	
<b>Bemerkungen:</b>	Streifen extrudiert gefertigt, Breite: 150mm bis 200mm, Kleben: keine Daten vorhanden	

Jederzeitige Änderungen vorbehalten. Es obliegt dem Besteller, vor Verwendung des Produktes selbst zu prüfen, ob es sich auf mögliche anwendungswirksame Einflüsse für den von ihm vorgesehenen Verwendungszweck eignet. Alle in diesem technischen Datenblatt enthaltenen Angaben stellen Richtwerte dar.

RESOGOOGO® GmbH & Co KG  
Rolandskoppel 17, D-24784 Westerrönfeld  
Tel: +49-4331-43818-0  
Fax: +49-4331-43818-28

Mail: [post@resogoo.com](mailto:post@resogoo.com), [www.resogoo.com](http://www.resogoo.com)



English: **Technical data sheet**      **TPE 10° A**

---

<b>0601</b>	<b>TPE 10° A - super soft; thickness: 2 - 8 mm</b>	<b>date: 07.12.2020</b>
<b>hardness:</b>	10° ± 5° Shore A; 8° Shore A (ISO 868 (3 sec.))	
<b>density (DIN EN ISO 1183-1A):</b>	0,99 g/ cm <sup>3</sup>	
<b>colour:</b>	black; colour possible	
<b>resistances</b>	ozone, weather, UV radiation: good <u>oils and fats:</u> ° vegetable-related: limited, ° animal-related: limited - no, ° mineral-related: no acids, bases, alcohol: good - limited fuels: no	
<b>remarks:</b>	strip extruded manufactured, width: 150mm to 200mm, bonding: no data available	

---

We reserve the right to make changes at any time. Before using the product, it is the responsibility of the purchaser to check for himself whether it is suitable for his intended use with regard to possible influences affecting the application. All data contained in this technical data sheet are approximate values.

---

**RESOGOO® GmbH & Co KG**  
Rolandskoppel 17, D-24784 Westerrönfeld  
**Tel: +49-4331-43818-0**  
**Fax: +49-4331-43818-28**

Mail: [post@resogoo.com](mailto:post@resogoo.com), [www.resogoo.com](http://www.resogoo.com)